

AET Lézaud GmbH, Am Hottenwald 8, 66606 St. Wendel

+49 (0)6851/97394 0 +49 (0)6851/97394 44 industrie@lezaud.de www.lezaud.de

Technical data sheet Status: 01.06.2021

sheets

LEZ-VIT 75/N

Pos	Parameter	Value	Unit	Norm
	Elastomer base	FKM with Nomex fabric		
	Geometry	Sheet		
	Density	1,84 +/-0,05	g/cm ³	ASTM D 297
	Hardness	75 +/-5	Shore A	ASTM D 2240
	Tensile strength	>= 7	MPa	ASTM D 412
	Elongation	>= 175	%	ASTM D 412
	Tensil strength	22	N/mm	ASTM D 624
	Compression set	30 at 175 °C; 22 h	%	ASTM D 395 Methode B
	Weight nomex	154 +/-55	g/m ²	
	Temperature	-15 to +200	°C	
	Color	black		

Pos*	Compliant	Addition
- - -		

Pos* A= Outside; IN= Inside, S1= Side1;;S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).