

AET Lézaud GmbH, Am Hottenwald 8, 66606 St. Wendel

☎ +49 (0)6851/97394 0 📠 +49 (0)6851/97394 44 ✉ [industrie@lezaud.de](mailto:industrie@lezaud.de) 🌐 [www.lezaud.de](http://www.lezaud.de)

Technical data sheet      Status:

sheets

## LEZ-VIT 75/S

Pos	Parameter	Value	Unit	Norm
	<b>Elastomer base</b>	<b>FKM with glass-fabric</b>		
	<b>Geometry</b>	<b>Sheet</b>		
	<b>Density</b>	<b>1,9 +/- 0,05</b>	<b>g/cm<sup>3</sup></b>	<b>DIN 53479</b>
	<b>Hardness</b>	<b>70 +/-5</b>	<b>Shore A</b>	<b>DIN 53505</b>
	<b>Tensile strength</b>	<b>&gt;= 2200</b>	<b>N/5cm</b>	<b>EN ISO 1421</b>
	<b>Temperature</b>	<b>-20 to +200</b>	<b>°C</b>	
	<b>Color</b>	<b>black</b>		
Pos*	Compliant	Addition		
	---			

Pos\* A= Outside; IN= Inside, S1= Side1,;S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose. We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).