

AET Lézaud GmbH, Am Hottenwald 8, 66606 St. Wendel

☎ +49 (0)6851/97394 0 📠 +49 (0)6851/97394 44 ✉ industrie@lezaud.de 🌐 www.lezaud.de

Technical data sheet Status: 01.06.2021

profiles

LEZ-VITMOOS CHEM

Pos	Parameter	Value	Unit	Norm
	Elastomer base	FKM		
	Geometry	Profile		
	Density	0,9	g/cm³	ASTM D 2240
	Hardness	30 +/-5	Shore A	ASTM D 2240
	Elongation at break	13	MPa	D 412
	Elongation	270	%	D 412
	Compression set	50 at 200°C; 22h	%	PV 3307
	Temperature	-10 to +200	°C	
	Color	black		
Pos*	Compliant	Addition		

Pos* A= Outside; IN= Inside, S1= Side1,;S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).