

AET Lézaud GmbH, Am Hottenwald 8, 66606 St. Wendel

☎ +49 (0)6851/97394 0 📠 +49 (0)6851/97394 44 ✉ industrie@lezaud.de 🌐 www.lezaud.de

Technical data sheet Status: 01.06.2021

sheets

LEZ-VITMOOS P10

Pos	Parameter	Value	Unit	Norm
	Elastomer base	FPM foamed		
	Geometry	Sheet		
	Density	0.2 to 0.3 depending on thickness		ASTM D 297
	Hardness	10-15	Shore A	ASTM D2240
	Compression set	13-27 depending on the strength at 24 ° C; 22 h	%	ASTM D 395 Methode D
	Compression set	100 at 70 ° C; 22 h	%	ASTM D 395 Methode D
	Temperature	-25 to +200	°C	
	Color	black		
Pos*	Compliant	Addition		

Pos* A= Outside; IN= Inside, S1= Side1,;S2= Side2

The values of these specifications come from regular controls of the compounds with the aid of norm samples and perform an average. They correspond to the actual state of the knowledge, the latest development of the sciences and our experience. They do not specify sure properties for the finals products. The indications in this data sheet are only a description of the typical properties and represent an aid and information for the user to give him some suggestions for his own application. But it remains in his responsibility to make sure with a specific trial that our product suits for his own purpose.

We strive to continuously improve our products. We reserve the right to modify and adjust the data sheet and our blends referring to the material properties. These will be documented with a new change status (date).